



**Table 37**

**RECTANGULAR AND REGULAR CROSS-SECTIONAL TOLERANCES  
(width, thickness, or diameter)**

For cored, rectangular, or other regular shapes of  
extruded, expanded, closed-cellular rubber.

RMA Class	1	2	3
RMA Drawing Designation	BER 1	BER 2	BER 3
Millimeters (Metric)			
Above - Included			
3.2 - 12.5	± 0.80	± 0.80	± 1.00
12.5 - 25.0	1.25	1.25	2.00
25.0 - 50.0	1.60	2.00	4.00
50.0 - 80.0	2.50	3.20	5.00
80.0 and over multiply by	0.06	0.08	0.10
RMA Class	1	2	3
RMA Drawing Designation	BER 1	BER 2	BER 3
Inches			
Above - Included			
.125 - .50	± 0.032	± 0.032	± 0.040
.50 - 1.0	0.050	0.500	0.080
1.0 - 2.0	0.063	0.080	0.160
2.0 - 3.15	0.100	0.125	0.200
3.15 and over multiply by	0.060	0.080	0.100