

NOTE: This chart is only a general guide. ELBEX cannot guarantee its accuracy nor assume any responsibility for its use thereof. It is recommended that testing is performed for specific applications.

Chemical	Polyisoprene (IR)	Natural Rubber (NR)	Styrene Butadiene (SBR)	Butyl (IIR)	Ethylene Propylene (EP, EPDM)	Nitrile (NBR)	Neoprene, Chloroprene (CR)	Silicone (VMQ)
Acetaldehyde	BC	B/U	U	A	A	U	U	AB
Acetamide	C/U	C/U	U	AB	A	A	AB	B
Acetic Acid 5%	B	B	B	A	A	B	A	A
Acetic Acid 30%	B	B	B	B	A	B	A	A
Acetic Acid, Hot & High Pressure	U	U	U	U	C	U	U	U
Acetic Acid, Glacial	BC	B/U	C	B	AB	U	U	B
Acetic Anhydride	BC	BC	C/U	B	B	B/U	AB	BC
Acetone	U	B/U	BC	A	A	U	C/U	BC
Acetophenone	C/U	C/U	U	AB	A	U	U	U
Acetyl Acetone	U	U	U	A	A	U	U	U
Acetyl Chloride	U	U	U	U	C	U	U	C
Acetylene	B	AB	BC	A	A	A	A	BC
Acetylene Tetrabromide	U	U	U	A/U	A	U	B	
Acrylonitrile	BC	BC	C	U	U	U	C/U	U
Adipic Acid	A	A		U	A	A	A	
Aero Lubriplate	U	U	B	U	U	A	A	B
Aero Safe 2300	U	U	U	B	A	U	U	C
Aero Safe 2300W	U	U	U	B	A	U	U	C
Aero Shell IAC	U	U	U	U	U	A	B	B
Aero Shell 7A Grease	U	U	U	U	U	A	B	B
Aero Shell 17 Grease	U	U	U	U	U	A	B	B
Aero Shell 750	U	U	U	U	U	B	U	
Aerozene 50 (50% Hydrazine 50% UDMH)	U	U	U	A	A	C	U	U
Air-Below 300 F	U	U	U	B	B	B	B	A
Air-Above 300 F	U	U	U	U	U	U	U	A
Alkazene	U	U	U	U	U	U	U	U
Alum-NH3Cr-K	A	A	A	A	A	A	A	A
Aluminum Acetate	A	A	B/U	B	A	B	B	U
Aluminum Bromide	A	A	A	A	A	A	A	A
Aluminum Chloride	A	A	A	A	A	A	A	B
Aluminum Fluoride	A	AB	A	A	A	A	A	B
Aluminum Nitrate	A	A	A	A	A	A	A	B
Aluminum Phosphate	A	A	A	A	A	A	A	A
Aluminum Salts	A	A	A	A	A	A	A	A
Aluminum Sulfate	A	A	B	A	A	A	A	A
Ambrex 33 Mobil	U	U	U	U	U	A	B	U
Amines, Mixed	AB	AB	B	B	AB	U	B/U	AB
Ammonia Anhydrous (Liquid)	U	U	B/U	A	A	AB	A	BC
Ammonia Gas, Cold	A	A	A	A	A	A	A	A
Ammonia Gas, Hot	C/U	C/U	U	B	B	B	B	A
Ammonia and Lithium Metal Solution	U	U	U	B	B	B	U	U
Ammonium Carbonate	A	A	A	A	A	AB	A	BC
Ammonium Chloride	A	A	A	A	A	AB	A	BC
Ammonium Hydroxide (Concentrated)	C/U	C/U	U	A	A	A/U	A	A
Ammonium Nitrate	A	A	A	A	A	A	A	BC
Ammonium Nitrite	AB	AB	A	A	A	A	A	B
Ammonium Persulfate Solution	A	A	U	A	B	A	A/U	
Ammonium Persulfate 10%	A	A	U	A	A	A	A	U
Ammonium Phosphate	A	A	A	A	A	A	A	A
Ammonium Phosphate, Monobasic	AC	A	A	A	A	A	A	A
Ammonium Phosphate, Dibasic	A	A	A	A	A	A	A	A

A: Recommended; Little or Minor Effect B: Minor to Moderate Effect C: Moderate to Severe Effect U: Unsatisfactory Blank: Insufficient Data

NOTE: This chart is only a general guide. ELBEX cannot guarantee its accuracy nor assume any responsibility for its use thereof. It is recommended that testing is performed for specific applications.

Chemical	Polyisoprene (IR)	Natural Rubber (NR)	Styrene Butadiene (SBR)	Butyl (IIR)	Ethylene Propylene (EP, EPDM)	Nitrile (NBR)	Neoprene, Chloroprene (CR)	Silicone (VMQ)
Ammonium Phosphate, Tribasic	AC	AB	A	A	A	A	A	A
Ammonium Salts	A	A	A	A	A	A	A	A
Ammonium Sulfate	A	A	B	A	A	A	A	A
Ammonium Sulfite	A	A	A	A	A	A	A	
Amyl Acetate	U	C/U	C/U	AB	A	U	U	U
Amyl Alcohol	AB	A	B	A	A	AB	A	U
Amyl Borate	U	U	U	U	U	AB	A	U
Amyl Chloranaphthalene	U	U	U	U	U	B/U	U	U
Amyl Chloride	U	U	U	U	U	U	U	U
Amyl Naphthalene	U	U	U	U	U	U	U	U
Anderol L-774 (diester)	U	U	U	U	U	A	U	U
Anderol L-826 (diester)	U	U	U	U	U	B	U	U
Anderol L-829 (diester)	U	U	U	U	U	B	U	U
Ang-25 (Diester Base) (TG749)	U	U	U	U	U	B	U	B
Ang-25 (Glycerol Ester)	B	B	B	B	A	B	B	B
Anhydrous Ammonia	U	U		U	A	AB	A	BC
Anhydrous Hydrazine	U	U	A	B	AB	U	B	B/U
Anhydrous Hydrogen Fluoride	U	U	U	A	AB	U	U	U
Aniline	U	U	U	A	AB	U	U	AB
Aniline Dyes	B	B	B	AB	AB	U	BC	A/U
Aniline Hydrochloride	AB	AB	C	B/U	B	U	U	C/U
Aniline Oils	U	U	U	AB	B	U	U	U
Animal Fats	U	B/U	U	BC	A	A	B	B
Animal Oils	U	U	U	B	A	A	AB	B/U
AN-O-3 Grade M	U	U	U	U	U	A	B	B
AN-O-6	U	U	U	U	U	A	B	U
AN-O-366	U	U	U	U	U	A	B	U
AN-VV-O-366b Hydraulic Fluid	U	U	U	U	U	A	B	U
Ansul Ether 161, 181	U	U	U	C	C	C	U	U
Aqua Regia	U	U	U	C/U	B	U	U	C/U
Argon	U	U	A/U	B	A	A	U	B
Arochlor 1248	U	U	U	B	B	C	U	B
Arochlor 1254	U	U	U	U	B	U	U	C
Arochlor 1260	A	A	A	A		A	A	A
Aromatic Fuel 50%	U	U	U	U	U	AB	U	U
Arsenic Acid	A	AB	A	A	A	A	A	A
Arsenic Trichloride	U	U		U	U	A	A	
Askarel Transformer Oil	U	U	U	U	U	B	U	U
Asphalt Emulsion	U	U	U	U	U	B	BC	U
ASTM Oil #1	U	U	U	U	U	A	A	A
ASTM Oil #2	U	U	U	U	U	A	B	A/U
ASTM Oil #3	U	U	U	U	U	A	U	C
ASTM Oil #4	U	U	U	U	U	B	BC	U
ASTM Reference Fuel A	U	U	U	U	U	A	B	U
ASTM Reference Fuel B	U	U	U	U	U	B/U	U	U
ASTM Reference Fuel C	U	U	U	U	U	B/U	U	U
ATL-857	U	U	U	U	U	B	U	U
Atlantic Dominion F	U	U	U	U	U	A	B	U
Aurex 903R Mobil	U	B	U	U	U	A	B	U
Automatic Transmission Fluid	U	U	U	U	U	A	B	U
Automotive Brake Fluid			A	B	A	C	B	A

A: Recommended; Little or Minor Effect B: Minor to Moderate Effect C: Moderate to Severe Effect U: Unsatisfactory Blank: Insufficient Data

NOTE: This chart is only a general guide. ELBEX cannot guarantee its accuracy nor assume any responsibility for its use thereof. It is recommended that testing is performed for specific applications.

Chemical	Polyisoprene (IR)	Natural Rubber (NR)	Styrene Butadiene (SBR)	Butyl (IIR)	Ethylene Propylene (EP, EPDM)	Nitrile (NBR)	Neoprene, Chloroprene (CR)	Silicone (VMQ)
Bardol B	U	U	U	U	U	U	U	U
Barium Chloride	A	A	A	A	A	A	A	A
Barium Hydroxide	A	A	A	A	A	A	A	A
Barium Salts	A	A	A	A	A	A	A	A
Barium Sulfate	A	A	A	A	A	A	A	A
Barium Sulfide	A	A	B	A	A	A	A	A
Bayol D	U	U	U	U	U	A	B	U
Beer	A	A	A	A	A	A	AB	A
Beet Sugar Liquors	A	A	A	A	A	A	AB	A
Benzaldehyde	U	U	U	AB	A	U	U	B/U
Benzene (Benzol)	U	U	U	U	U	U	U	U
Benzenesulfonic Acid	U	U	U	U	U	U	AB	U
Benzine (Gasoline; Ligroin)	U	U	U	U	U	A	B	U
Benzochloride	U	U	U	B	A	U	U	
Benzoic Acid	B/U	B/U	U	A/U	A/U	U	A	B/U
Benzophenone	U		U	B	B	A/U		U
Benzyl Alcohol	C/U	U	U	AB	B	U	B/U	
Benzyl Benzoate	U	U	U	B	B	U	U	
Benzyl Chloride	U	U	U	U	U	U	U	U
Black Furnace Gas	U	U	U	C/U	U	U	U	A
Black Point 77	C	C	C	A	A	A	C	C
Black Sulphate Liquor	AB	AB	B	AB	AB	AB	AB	AB
Bleach Solutions	U	U	B/U	AB	A	U	U	B
Borax	AB	AB	B	A	A	AB	A	B
Bordeaux Mixture	AC	AB	B	A	A	A	AB	B
Boric Acid	A	A	A	A	A	A	A	A
Boron Fluids (HEF)	U	U	U	U	U	B	U	U
Brake Fluid		U	A	A	A	U	B	C
Bray GG-130	U	U	U	B/U	U	B	U	U
Brayco 719-R (VV-H-910)	B	B		B	A	C	B	B
Brayco 885 (MIL-L-6085A)	U	U	U	U	U	B	U	U
Brayco 910	A	A	B	A	A	B	B	U
Bret 710	A	A	B	A	A	B	B	U
Brine	A	A		A	A	A	AB	A
Brom-113			U	U	U	C	U	U
Brom-114	U	U	U	U	U	B	B	U
Bromine Gas	U	U	U	U	U	U	U	U
Bromine Liquid		U			U	U	U	C
Bromine Pentafluoride	U	U	U	U	U	U	U	U
Bromine Trifluoride	U	U	U	U	U	U	U	U
Bromine Water	U	U	U	U	U	U	B/U	U
Bromobenzene	U	U	U	U	U	U	U	U
Bromochlorotrifluoromethane	U	U	U	U	U	U	U	U
Bunker Oil	U	U	U	U	U	A	B/U	B/U
Butadiene (Monomer)	U	U	U	A/U	A/U	A/U	B/U	U
Butane	U	U	C/U	U	U	A	AC	U
Butane 2,2-Dimethyl	U	U	C	U	U	A	B	U
Butane 2,3-Dimethyl	U	U	C	U	U	A	B	U
Butanol (Butyl Alcohol)	A	A	A	B	AB	A	A	B
1-Butene, 2-Ethyl	U	U	U	U	U	A	B/U	U
Butter	U	U	U	BC	A	A	B	AB

A: Recommended; Little or Minor Effect B: Minor to Moderate Effect C: Moderate to Severe Effect U: Unsatisfactory Blank: Insufficient Data

NOTE: This chart is only a general guide. ELBEX cannot guarantee its accuracy nor assume any responsibility for its use thereof. It is recommended that testing is performed for specific applications.

Chemical	Polyisoprene (IR)	Natural Rubber (NR)	Styrene Butadiene (SBR)	Butyl (IIR)	Ethylene Propylene (EP, EPDM)	Nitrile (NBR)	Neoprene, Chloroprene (CR)	Silicone (VMQ)
Butyl Acetate	U	U	U	BC	U	U	U	U
Butyl Acetyl Ricinoleate	U	U	U	A	A	BC	B	
Butyl Acrylate	U	U	U	U	A/U	U	U	A
Butyl Alcohol	A	A	A	B	AB	A	A	B
Butyl Amine	U	U	U	U	A/U	A/U	U	B
n-Butyl Benzoate	U	U	U	A	A	U	U	
n-Butyl Butyrate	U	U	U	A	A	U	U	
Butyl Carbitol	U	U	U	A	A	U	C	U
Butyl Cellosolve	U	U	U	A	A	C	U	U
Butyl Cellosolve Adipate	U	U	U	B	B	U	U	B
n-Butyl Ether	U	U	U	C/U	C/U	B/U	B/U	U
Butyl Oleate	U	U	U	B	B	U	U	B
Butyl Stearate	U	U	U	B/U	B/U	B	U	
Butylene	U	U	U	U	U	A	BC	U
Butyraldehyde	U	U	U	B	BC	U	B/U	U
Butyric Acid	C	C/U	U	B	AB	U	U	U
Calcine Liquors				A	A	A		
Calcium Acetate	A	A	U	A	A	AB	B	U
Calcium Bisulfite	C/U	A/U	U	B/U	B/U	A	A	A
Calcium Carbonate	A	A	A	A	A	A	A	AC
Calcium Chloride	A	A	A	A	A	A	A	A
Calcium Cyanide	A	A	A	A	A	A	A	A
Calcium Hydroxide	A	A	A	A	A	A	A	A
Calcium Hypochloride	U	U	U	A	A	U	U	
Calcium Hypochlorite	B/U	B/U	B/U	A	A	B/U	BC	B
Calcium Nitrate	A	A	A	A	A	A	A	AB
Calcium Phosphate	A	A	A	A	A	A	B	A
Calcium Salts	A	A	A	A	A	A	A	B
Calcium Silicate	A	A	A	A	A	A	A	
Calcium Sulfide	B/U	B/U	B/U	A	A	A	A	AB
Calcium Sulfite	AB	AB	B	A	A	A	A	A
Calcium Thiosulfate	B	B	B	A	A	B	A	A
Caliche Liquors	A	A	A	A	A	A	A	B
Cane Sugar Liquors	A	A	A	A	A	A	A	A
Caprilic Aldehyde	B/U	B/U		B	B	U	BC	B
Carbamate	U	U	U	B	B	C	B	
Carbitol	B/U	B/U	B	A	AB	AB	BC	B
Carbolic Acid	U	U	U	B	U	U	U	U
Carbon Bisulfide	U	U	U	U	U	C/U	U	U
Carbon Dioxide, Dry	B	B	B	B	B	A	AB	B
Carbon Dioxide, Wet	B	B	B	AB	AB	A	B	B
Carbon Disulfide	U	U	U	U	U	C/U	U	U
Carbon Monoxide	B	BC	B	A	A	A	A	A
Carbon Tetrachloride	U	U	U	U	B/U	C/U	U	U
Carbonic Acid	A	A	B	A	A	AB	AB	A
Castor Oil	A	A	A	B	AB	A	A	A
Cellosolve	U	U	U	B	B	C/U	U	U
Cellosolve Acetate	C/U	U	U	B	AB	U	U	U
Cellosolve Butyl	U	U	U	B	AB	U	U	U
Celluguard	A	A	A	A	A	A	A	A
Cellulube A60 (Fyrquel)	U	U	B/U	B	AB	U	C/U	C

A: Recommended; Little or Minor Effect B: Minor to Moderate Effect C: Moderate to Severe Effect U: Unsatisfactory Blank: Insufficient Data

NOTE: This chart is only a general guide. ELBEX cannot guarantee its accuracy nor assume any responsibility for its use thereof. It is recommended that testing is performed for specific applications.

Chemical	Polyisoprene (IR)	Natural Rubber (NR)	Styrene Butadiene (SBR)	Butyl (IIR)	Ethylene Propylene (EP, EPDM)	Nitrile (NBR)	Neoprene, Chloroprene (CR)	Silicone (VMQ)
Cellulube 90, 100, 150, 220, 300, 500	C/U	B/U	U	A	A	U	U	A
Cellutherm 2505A	U	U	U	U	U	B	U	U
Cetane (Hexadecane)	U	U	U	U	U	A	B	U
China Wood Oil (Tung Oil)	U	U	U	B/U	U	A	A	U
Chloroacetic Acid	U	U	U	B	AB	U	A	C/U
Chlordane	U	U	U	U	U	B	C	U
Chlorextol	U	U	U	U	U	B	B	U
Chlorinated Salt Brine	B	B	U	U	U	U	U	U
Chlorinated Solvents, Dry	U	U	U	U	U	U	U	U
Chlorinated Solvents, Wet	U	U	U	U	U	U	U	U
Chlorine, Dry	C/U	B/U	U	C/U	A/U	C/U	C/U	U
Chlorine, Wet	U	C/U	C/U	C/U	B/U	C/U	C/U	U
Chlorine Dioxide	U	U	U	C/U	C	U	U	AC
Chlorine Trifluoride	U	U	U	U	U	U	U	U
Chloroacetic Acid	B/U	B/U	U	B	AB	U	U	B/U
Chloroacetone	B/U	B/U	U	BC	A	U	C	U
Chlorobenzene, Mono, Di, Tri	U	U	U	U	U	U	U	U
Chlorobromomethane	U	U	U	B	B	U	U	U
Chlorobutadiene	U	U	U	U	U	U	U	U
Chlorododecane	U	U	U	U	U	U	U	U
Chloroform	U	U	U	U	U	U	U	U
O-Chloronaphthalene	U	U	U	U	U	U	U	U
1-Chloro 1- Nitro Ethane	U	U	U	U	U	U	U	U
Chlorosulfonic Acid, Dry	U	U	U	U	U	U	U	U
Chlorosulfonic Acid, Wet	U	U	U	U	C	U	U	U
Chlorotoluene	U	U	U	U	U	U	U	U
Chlorox	U	U	U	AB	B	B	B	
O-Chlorphenol	U	U	U	U	U	U	U	U
Chrome Alum	A	A	A	A	A	A	A	A
Chrome Plating Solutions	U	U	U	U	U	U	U	B
Chromic Acid	U	U	U	BC	U	U	U	C
Chromic Oxide .88 Wt.% Aqueous Solution	U	U	U	B	B	U	U	B
Circo Light Process Oil	U	U	U	U	U	A	B	U
Citric Acid	A	A	A	A	A	A	A	A
City Service Koolmotor-AP Gear Oil 140-E.P.I.	U	U	U	U	U	A	B	U
City Service Pacemaker #2	U	U	U	U	U	A	B	U
City Service #65,#120,#250	U	U	U	U	U	A	B	U
Cobalt Chloride	A	A	A	A	A	A	A	B
Coconut Oil	U	U	U	AB	B	A	AC'	A
Cod Liver Oil	U	U	U	A	A	A	B	B
Coffee	A	A	A	A	A	A	A	A
Coke Oven Gas	C/U	B/U	U	U	A/U	B/U	C/U	B
Coliche Liquors	A	A	B	B	B	B	A	
Convelex 10	U	U	U	U		U	U	U
Coolanol (Monsanto)	U	U	U	U	U	A	AB	U
Coolanol 25, 45 (Monsanto)	U	U	U	U	C/U	A	A	U
Copper Acetate	A	A	U	A	A	B	B	U
Copper Chloride	A	AB	A	A	A	A	AB	A
Copper Cyanide	A	A	A	A	A	A	A	A
Copper Salts	A	A	A	A	A	A	A	A
Copper Sulfate	BC	B	B	B	A	A	A	A

A: Recommended; Little or Minor Effect B: Minor to Moderate Effect C: Moderate to Severe Effect U: Unsatisfactory Blank: Insufficient Data

NOTE: This chart is only a general guide. ELBEX cannot guarantee its accuracy nor assume any responsibility for its use thereof. It is recommended that testing is performed for specific applications.

Chemical	Polyisoprene (IR)	Natural Rubber (NR)	Styrene Butadiene (SBR)	Butyl (IIR)	Ethylene Propylene (EP, EPDM)	Nitrile (NBR)	Neoprene, Chloroprene (CR)	Silicone (VMQ)
Corn Oil	U	U	U	AB	B/U	A	AC	A
Cottonseed Oil	U	U	U	AC	A	A	AC	A
Creosols (2-Methyl - 4 Methylphenyl)	U	U	U	U	U	U	U	U
Creosote	U	U	U	U	U	AB	U	U
Creosote, Coal Tar	U	U	U	U	U	AB	B/U	C/U
Creosote, Wood Tar	U	U	U	U	U	A	BC	C/U
Cresols (M, O, and P)	U	U	U	U	U	C/U	C/U	B/U
Cresylic Acid	U	U	U	U	U	C/U	U	
Crude Oil	U	U	U	U	U	B	C/U	U
Cumene	U	U	U	U	A/U	U	B/U	U
Cutting Oil	U	U	U	U	U	A	B	U
Cyclohexane	U	U	U	U	U	AB	U	U
Cyclohexanol	B/U	B/U	U	U	C/U	AB	AB	U
Cyclohexanone	U	U	U	B/U	BC	U	U	U
p-Cymene	U	U	U	U	U	U	U	U
Decalin	U	U	U	U	U	U	U	U
Decane	U	U	U	U	U	AB	C/U	B
Delco Brake Fluid			A	B	A	C	B	C
Denatured Alcohol	A	A	A	A	A	A	A	A
Detergent Solutions			AB	A	A	A	AB	
Developing Fluids	A	A	B	B	AB	A	A	AB
Dextron	U	U	U	U	U	A	B	U
Diacetone	C/U	C/U	U	A	A	U	U	U
Diacetone Alcohol	B/U	B/U	C/U	A	A	U	A/U	A/U
Diazinon (Pesticide)	U	U	U	U	U	C	C	U
Dibenzyl Ether	U	U	U	B	BC	U	U	
Dibenzyl Sebacate	U	U	U	B	B	U	U	C
Dibromoethyl Benzene (Alkazene)	U	U	U	U	U	U	U	U
Dibutylamine	U	U	U	U	U	U	C/U	C
Dibutyl Ether	U	U	U	C/U	C/U	B/U	B/U	U
Dibutyl Phthalate	U	U	U	BC	A	U	U	B
Dibutyl Sebacate	U	U	U	B	B	U	U	B
O-Dichlorobenzene	U	U	U	U	U	U	U	U
P-Dichlorobenzene	U	U	U	U	U	U	U	U
Dichlorobutane	U	U	U	U	U	B	U	U
Dichloro-Isopropyl Ether	U	U	U	C/U	C	U	U	U
Dicyclohexylamine	U	U	U	U	U	C/U	U	U
Diesel Oil	U	U	U	U	U	A	B/U	U
Diester Lubricant MIL-L-7808	U	U	U	U	U	AB	U	U
Diester Synthetic Lubricants	U	U	U	U	U	B/U	U	U
Diethyl Ether	U	U	U	U	U	U	U	U
Diethyl Sebacate	U	U	U	B	B	U	U	B
Diethylamine	B	B	B	B	B	BC	B	B
Diethylbenzene	U	U	U	U	U	U	U	U
Diethylene Glycol	A	A	A	A	A	A	A	B
Difluorodibromomethane	U	U	U	B	B	U	U	U
Diisobutylene	U	U	U	U	U	A	B/U	U
Diisooctyl Sebacate	U	U	U	U	C	C	U	C
Diisopropyl Benzene	U	U	U	U	U	U	U	U
Diisopropyl Ketone	U	U	U	A	A	U	U	U
Dimethylaniline	U	U	U	A/U	AB	U	U	U

A: Recommended; Little or Minor Effect B: Minor to Moderate Effect C: Moderate to Severe Effect U: Unsatisfactory Blank: Insufficient Data

NOTE: This chart is only a general guide. ELBEX cannot guarantee its accuracy nor assume any responsibility for its use thereof. It is recommended that testing is performed for specific applications.

Chemical	Polyisoprene (IR)	Natural Rubber (NR)	Styrene Butadiene (SBR)	Butyl (IIR)	Ethylene Propylene (EP, EPDM)	Nitrile (NBR)	Neoprene, Chloroprene (CR)	Silicone (VMQ)
Dimethylbenzene	U	U	U	U	U	U	U	U
Dimethylcarbinol	A	A		A	B	B	A	A
Dimethylether	AU	AU	A	AC	AB	A	C	A
Dimethylformamide	U	U	U	B	AB	B/U	U	BC
Dinitrochlorobenzene (DCNB)			U		U	U	U	U
Dinitrotoluene	U	U	U	U	U	U	U	U
Diocetyl Phthalate (DOP)	U	U	U	B	B	U	U	C
Diocetyl Sebacate	U	U	U	AB	B	U	U	C
Dioxane	U	U	U	AB	AB	U	U	U
Dioxolane	U	U	U	C/U	B	U	U	U
Dipentene	U	U	U	U	U	AB	U	U
Diphenyl	U	U	U	U	U	U	U	U
Diphenyl Oxides	U	U	U	U	U	U	U	C
Dow Chemical 50-4			A	B	A	C	BC	
Dow Chemical ET378	U	U	U	U		U	U	U
Dow Chemical ET588			A	B	A	C	BC	
Dow Corning-3	A	A	A	A	A	A	A	C
Dow Corning-4	A	A	A	A	A	A	A	C
Dow Corning-5	A	A	A	A	A	A	A	C
Dow Corning-11	A	A	A	A	A	A	A	C
Dow Corning-33	A	A	A	A	A	A	A	C
Dow Corning-44	A	A	A	A	A	A	A	C
Dow Corning-55	A	A	A	A	A	A	A	C
Dow Corning-200	A	A	A	A	A	A	A	C
Dow Corning-220	A	A	A	A	A	A	A	C
Dow Corning-510	A	A	A	A	A	A	A	C
Dow Corning-550	A	A	A	A	A	A	A	C
Dow Corning-705	A	A	A	A	A	A	A	C
Dow Corning-710	A	A	A	A	A	A	A	C
Dow Corning-1208	A	A	A	A	A	A	A	C
Dow Corning-4050	A	A	A	A	A	A	A	C
Dow Corning-6620	A	A	A	A	A	A	A	C
Dow Corning-F60	A	A	A	A	A	A	A	C
Dow Corning-F61	A	A	A	A	A	A	A	B
Dow Corning-XF60	A	A	A	A	A	A	A	C
Dow Guard	A	A	A	A	A	A	A	A
Dowtherm 209, 50% Solution				B	A	C	B	C
Dowtherm A	U	U	U	U	U	U	U	B/U
Dowtherm E	U	U	U	U	U	U	U	A/U
Dowtherm Oil	U	U	U	U	U		U	B
Drinking Water	A	A	A	A	A	A	AB	A
Dry Cleaning Fluids	U	U	U	U	U	C	U	U
DTE Light Oil	U	U	U	U	U	A	B	U
Elco 28-EP Lubricant	U	U	U	U	U	A	C	B
Epichlorohydrin	U	U	U	B	BC	U	U	U
Epoxy Resins				A	A		A	
Esam-6 Fluid			A	B	A		B	
Esso Fuel 208	U	U	U	U	U	A	B	U
Esso Golden Gasoline	U	U	U	U	U	B	U	U
Esso Motor Oil	U	U	U	U	U	A	C	U
Esso Transmission Fluid (Type A)	U	U	U	U	U	A	B	U

A: Recommended; Little or Minor Effect B: Minor to Moderate Effect C: Moderate to Severe Effect U: Unsatisfactory Blank: Insufficient Data

NOTE: This chart is only a general guide. ELBEX cannot guarantee its accuracy nor assume any responsibility for its use thereof. It is recommended that testing is performed for specific applications.

Chemical	Polyisoprene (IR)	Natural Rubber (NR)	Styrene Butadiene (SBR)	Butyl (IIR)	Ethylene Propylene (EP, EPDM)	Nitrile (NBR)	Neoprene, Chloroprene (CR)	Silicone (VMQ)
Esso WS3812 (MIL-L-7808A)	U	U	U	U	U	AB	U	U
Esso XP90-EP Lubricant	U	U	U	U	U	A	B	U
Esstic 42,43	U	U	U	U	U	A	B	U
Ethane	U	U	U	U	U	A	B	U
Ethanolamine	B	B	B/U	B	AB	B	B	B
Ethers	U	U	U	U	C	B/U	U	U
Ethyl Acetate (Organic Ester)	U	U	U	B	A	U	U	B
Ethyl Acetoacetate	C	BC	C	B	AB	U	U	B
Ethyl Acrylate	U	U	U	B	B	U	U	B
Ethyl Acrylic Acid	U	U	U	B	B	U	B	U
Ethyl Alcohol	A	A	A	A	A	A	A	B
Ethyl Benzene	U	U	U	U	U	U	U	U
Ethyl Benzoate	U	U	U	U	B/U	U	U	U
Ethyl Bromide	B/U	B/U	U	U	U	B	U	U
Ethyl Cellosolve	B/U	B/U	U	AB	AB	AB	C/U	U
Ethyl Cellulose	B	B	B	B	B	B	B	BC
Ethyl Chloride	BC	B/U	B	A	A	A	U	C/U
Ethyl Chlorocarbonate	U	U	U	U	U	U	U	U
Ethyl Chloroformate	U	U	U	U	U	U	U	U
Ethyl Cyclopentane	U	U	U	U	U	A	C	U
Ethyl Ether	U	U	U	C/U	U	U	U	U
Ethyl Formate	U	U	U	B	B	U	B	
Ethyl Hexanol	A	A	A	A	A	A	A	B
Ethyl Mercaptan	U	U	U	U	A/U	U	C/U	C
Ethyl Oxalate	A	A/U	U	U	A/U	U	U	U
Ethyl Pentachlorobenzene	U	U	U	U	U	U	U	U
Ethyl Silicate	B	B	B	A	A	A	A	
Ethylene			U	AB	C/U	A	AC	B/U
Ethylene Chloride	U	U	U	C/U	C/U	U	U	U
Ethylene Chlorohydrin	B	B	B	AB	AB	U	B	C
Ethylene Diamine	AB	AB	B	A	A	AB	A	A
Ethylene Dibromide	U	U	U	C/U	BC	U	U	U
Ethylene Dichloride	U	U	U	BC	C/U	U	U	U
Ethylene Glycol	A	A	A	A	A	A	A	A
Ethylene Oxide	U	U	U	C/U	A/U	U	U	U
Ethylene Trichloride	U	U	U	C	C/U	U	U	C/U
Ethylmorpholene Stannous Octoate (50/50 mix)			U	B	B	U		
F-60 Fluid (Dow Corning)	A	A	A	A	A	A	A	U
F-61 Fluid (Dow Corning)	A	A	A	A	A	A	A	U
Fatty Acids	C/U	C/U	U	C/U	C/U	A	B	C
FC-43 Heptacosofluorotributylamine			U	A	A	A	A	A
FC-75 Fluorocarbon			U	A	A	A	A	A
Ferric Chloride	A	A	A	A	A	A	A	AB
Ferric Nitrate	A	A	A	A	A	A	A	BC
Ferric Sulfate	A	A	A	A	A	A	A	BC
Fish Oil			U		U	A	AB	A
Fluoroboric Acid	A	A	A	AB	A	A	A	A
Fluorine (Liquid)	U	U		C/U	C/U	U	C/U	U
Fluorobenzene	U	U	U	U	U	U	U	U
Fluorocarbon Oils				A	A		A	
Fluorolube	U	U	U	A	A	A	A	A

A: Recommended; Little or Minor Effect B: Minor to Moderate Effect C: Moderate to Severe Effect U: Unsatisfactory Blank: Insufficient Data

NOTE: This chart is only a general guide. ELBEX cannot guarantee its accuracy nor assume any responsibility for its use thereof. It is recommended that testing is performed for specific applications.

Chemical	Polyisoprene (IR)	Natural Rubber (NR)	Styrene Butadiene (SBR)	Butyl (IIR)	Ethylene Propylene (EP, EPDM)	Nitrile (NBR)	Neoprene, Chloroprene (CR)	Silicone (VMQ)
Fluorinated Cyclic Ethers		U		A	A	U	U	
Fluorosilicic Acid	A	A	AB	A	A	A	A	A/U
Formaldehyde	B		AC	A	A	BC	AB	B
Formic Acid	AC	AC	A	A	A	B/U	A	BC
Freon, 11	U	U	U	U	U	AB	U	U
Freon, 12	U	B/U	A	B/U	BC	A	A	U
Freon, 12 and ASTM Oil #2 (50/50 mix)	U	U	U	U	U	A	AB	U
Freon, 12 and Sunisco 4G (50/50 mix)	U	U	U	U	U	A	B	U
Freon, 13	A/U	A/U	A	A	A	A	A	U
Freon, 13B1	A/U	A/U	A	A	A	A	A	U
Freon, 14	U	A/U	A	A	A	A	A	U
Freon, 21	U	U	U	U	U	U	B/U	U
Freon, 22	A/U	A/U	A	C/U	A	U	A	U
Freon, 22 and ASTM Oil #2 (50/50 mix)		U	U	U	U	U	B	U
Freon, 31	B	B	B	A	A	U	A	
Freon, 32	A	A	A	A	A	A	A	
Freon, 112	U	U	U	U	U	AB	B	U
Freon, 113	C/U	C/U	B	U	U	A	A	U
Freon, 114	A/U	A/U	A	A/U	A	U	A	U
Freon, 114B2	U	U	U	U	U	AB	A	U
Freon, 115	A	A	A	A	A	A	A	U
Freon, 142b	A	A	A	A	A	A	A	
Freon, 152a	A	A	A	A	A	A	A	
Freon, 218	A	A	A	A	A	A	A	
Freon, C316	A	A	A	A	A	A	A	
Freon, C318	A	A	A	A	A	A	A	
Freon, 502	A	A	A	A	A	B	A	
Freon, BF	U	U	U	U	U	AB	B	U
Freon, MF	U	U	U	U	U	AB	U	U
Freon, TA	C/U	C/U	A	A	A	A	A	A
Freon, TC	U	U	B	A	B	A	A	U
Freon, TF	U	U	B	U	U	A	A	U
Freon, TMC	B	B	C	B	B	B	B	C
Freon, T-P35	A	A	A	A	A	A	A	A
Freon, T-WD602	C	C	B	A	B	B	B	U
Freon, PCA		U	B	U	U	A	A	U
Fuel Oil	U	U	U	U	U	A	B	U
Fuel Oil, Acidic	U	U	U	U	U	A	B	A
Fuel Oil, #6	U	U	U	U	U	B	U	A
Fumaric Acid	AB	AB	AB	U	B	A	B	B
Fuming Sulphuric Acid (20-25% Oleum)	U	U	U	U	U	U	U	U
Furan (Furfuran)	U	U	U	U	C/U	U	U	U
Furfural	U	U	U	A	AB	U	BC	C/U
Furfuraldehyde	U	U	U	B	AB	U	BC	C/U
Furfuryl Alcohol	U	U	U	B	B	U	U	U
Furyl Carbinol	U	U	U	B	B	U	U	U
Fyrquel A60	U	U	U	B	B	U	U	C
Fyrquel 90,100,150,220,300,500,550	U	U	U	A	A	U	U	A
Gallic Acid	A	A	B	B	AB	AB	B	
Gasoline	U	U	U	U	U	A	B/U	U
Gelatin	A	A	A	A	A	A	A	A

A: Recommended; Little or Minor Effect B: Minor to Moderate Effect C: Moderate to Severe Effect U: Unsatisfactory Blank: Insufficient Data

NOTE: This chart is only a general guide. ELBEX cannot guarantee its accuracy nor assume any responsibility for its use thereof. It is recommended that testing is performed for specific applications.

Chemical	Polyisoprene (IR)	Natural Rubber (NR)	Styrene Butadiene (SBR)	Butyl (IIR)	Ethylene Propylene (EP, EPDM)	Nitrile (NBR)	Neoprene, Chloroprene (CR)	Silicone (VMQ)
Girling Brake Fluid			A	B	A	C	B	
Glacial Acetic Acid	BC	B/U	BC	B	AB	U	C/U	B
Glauber's Salt	AB	AB	B	A	A	A	A	A
Glucose	AB	A	A	A	A	A	AB	A
Glue (Depending on type)	AB	AB	A	A	A	A	A	A
Glycerin or Glycerol	A	A	A	A	A	A	A	A
Glycols, General	A	A	A	A	A	A	A	A
Green Sulfate Liquor	AB	AB	B	A	A	B	B	A
Gulf Endurance Oils	U	U	U	U	U	A	B	U
Gulf FR Fluids (Emulsion)	U	U	U	U	U	A	B	U
Gulf FRG-Fluids	A	A	A	A	A	A	A	A
Gulf FRP-Fluids	U	U	U	B	B	U	U	A
Gulf Harmony Oils	U	U	U	U	U	A	B	U
Gulf High Temperature Grease	U	U	U	U	U	A	B	U
Gulf Legion Oils	U	U	U	U	U	A	B	U
Gulf Paramount Oils	U	U	U	U	U	A	B	U
Gulf Security Oils	U	U	U	U	U	A	B	U
Gulfcrown Grease	U	U	U	U	U	A	B	U
Halothane	U	U	U	U	U	U	U	U
Halowax Oil	U	U	U	U	U	U	U	U
Hannifin Lube A	U	U	B	U	U	A	A	B
Heavy Water	A	A	A	A	A	A	B	A
HEF-2 (High Energy Fuel)	U	U	U	U	U	B	U	U
Helium	A	A	A	A	A	A	A	A
N-Heptane	U	U	U	U	U	A	AB	U
n-Hexaldehyde	U	U	U	AB	A	U	A	B
Hexane	U	U	U	U	U	A	B	U
n-Hexene-1	U	U	U	U	U	B	B	U
Hexyl Alcohol	A	A	A	BC	AB	B	B	B
High Viscosity Lubricant, H2			A	A	A	A	B	A
High Viscosity Lubricant, U4			A	A	A	A	B	A
Hi-lo MS #1	U	U	U	B	A	U	U	C
Houghto-Safe 271 (Water and Glycol base)		A	A	B	A	A	B	B
Houghto-Safe 620 (Water/Glycol)		A	A	B	A	A	B	B
Houghto-Safe 1010, Phosphate Ester	U	U	U	A	A	U	U	C
Houghto-Safe 1055, Phosphate Ester	U	U	U	A	A	U	U	C
Houghto-Safe 1120, Phosphate Ester	U	U	U	A	A	U	U	C
Houghto-Safe 5040 (Water/Oil Emulsion)	U	U	U	U	U	A	B	C
Hydraulic Oil (Petroleum Base)	U	U	U	U	U	A	B	BC
Hydrazine	U	U	B	A	A	B	B	B/U
Hydrobromic Acid	A	A	U	A	A	U	C/U	U
Hydrobromic Acid 40%	AB	A	U	A	A	U	B	U
Hydrocarbon (Saturated)	U	U	U	U	U	A	B	U
Hydrochloric Acid 37%, Cold	B	B	B	A	BC	AB	AB	B/U
Hydrochloric Acid 37%, Hot	U	U	U	C	C/U	C/U	BC	U
Hydrochloric Acid 3 Molar	C	C	C	A	A	C	C	U
Hydrochloric Acid Concentrated	U	U	U	A	C	U	U	U
Hydrocyanic Acid	AB	AB	B	A	A	B	B	AC
Hydro-Drive, MIH-10 (Petroleum Base)	U	U	U	U	U	A	B	B
Hydro-Drive, MIH-50 (Petroleum Base)	U	U	U	U	U	A	B	B
Hydrofluoric Acid, 65% Max. Cold	BC	BC	B	A	AB	B	A	B/U

A: Recommended; Little or Minor Effect B: Minor to Moderate Effect C: Moderate to Severe Effect U: Unsatisfactory Blank: Insufficient Data

NOTE: This chart is only a general guide. ELBEX cannot guarantee its accuracy nor assume any responsibility for its use thereof. It is recommended that testing is performed for specific applications.

Chemical	Polyisoprene (IR)	Natural Rubber (NR)	Styrene Butadiene (SBR)	Butyl (IIR)	Ethylene Propylene (EP, EPDM)	Nitrile (NBR)	Neoprene, Chloroprene (CR)	Silicone (VMQ)
Hydrofluoric Acid, 65% Min. Cold	U	U	U	C	C	U	U	U
Hydrofluoric Acid, 65% Max. Hot	U	U	U	U	U	U	C	U
Hydrofluoric Acid, 65% Min. Hot	U	U	U	U	U	U	U	U
Hydrofluosilicic Acid	A	A	B	A	A	AB	B	A/U
Hydrogen Gas, Cold	AB	B	B	A	A	A	A	C
Hydrogen Gas, Hot	B	B	B	A	A	A	A	C
Hydrogen Peroxide	B	B	B	A	A	B	A	A
Hydrogen Peroxide 90%	U	U	U	C/U	BC	U	U	B
Hydrogen Sulfide Dry, Cold	A	A	A	A	A	A	A	C/U
Hydrogen Sulfide Dry, Hot	U	U	U	AB	B	B	B	C/U
Hydrogen Sulfide Wet, Cold	C/U	C/U	U	A	A	B/U	A	C/U
Hydrogen Sulfide Wet, Hot	U	U	U	AB	B	U	B	C
Hydrolube (Water/Ethylene Glycol)			A	B	A	A	B	B
Hydroquinone	B	B	U	U	A/U	C/U	U	
Hydrene	B	B	B	B	A	B	B	U
Hyjet	U	U	U	B	A	U	U	
Hyjet III	U	U	U	B	A	U	U	
Hyjet S	U	U	U	B	A	U	U	
Hyjet W	U	U	U	B	A	U	U	
Hypochlorous Acid	B	B	U	B	B	U	U	U
Industron FF44	U	U	U	U	U	A	B	U
Industron FF48	U	U	U	U	U	A	B	U
Industron FF53	U	U	U	U	U	A	B	U
Industron FF80	U	U	U	U	U	A	B	U
Iodine	U	U	B	B	AB	B	U	C
Iodine Pentafluoride	U	U	U	U	U	U	U	U
Iodoform		B		A	A		U	
Isobutyl Alcohol	A	A	A	A	A	B	A	A
Isobutyl n-Butyrate	U	U	U	A	A	U	U	
Isododecane	U	U	U	U	U	A	B	U
Isooctane	U	U	U	U	U	A	B	U
Isophorone (Ketone)	U	U	U	A	A	U	U	U
Isopropanol	A	A	A	A	A	A	AB	A
Isopropyl Acetate	U	U	U	AB	AB	U	U	U
Isopropyl Alcohol	AB	A	A	A	A	A	AB	A
Isopropyl Chloride	U	U	U	U	U	U	U	U
Isopropyl Ether	U	U	U	U	U	AB	U	U
JP-3 (MIL-J-5624)	U	U	U	U	U	A	U	U
JP-4 (MIL-J-5624)	U	U	U	U	U	A	U	U
JP-5 (MIL-J-5624)	U	U	U	U	U	A	U	U
JP-6 (MIL-J-25656)	U	U	U	U	U	A	U	U
JP-X (MIL-F-25604)	U	U	U	U	U	A	B	U
Kel-F Liquids			A	A	A	A		A
Kerosene	U	U	U	U	U	A	BC	U
Keystone #87HX Grease	U	U	U	U	U	A	U	U
Lacquer Solvents	U	U	U	U	U	U	U	U
Lacquers	U	U	U	U	U	U	U	U
Lactams (Amino Acids)	U	U	U	B	B	U	B	
Lactic Acid, Cold	A	A	A	A	A	A	A	A
Lactic Acid, Hot	U	U	U	U	AB	A/U	AC	B
Lactones (Cyclic Esters)	U	U	U	B	B	U	U	B

A: Recommended; Little or Minor Effect B: Minor to Moderate Effect C: Moderate to Severe Effect U: Unsatisfactory Blank: Insufficient Data

NOTE: This chart is only a general guide. ELBEX cannot guarantee its accuracy nor assume any responsibility for its use thereof. It is recommended that testing is performed for specific applications.

Chemical	Polyisoprene (IR)	Natural Rubber (NR)	Styrene Butadiene (SBR)	Butyl (IIR)	Ethylene Propylene (EP, EPDM)	Nitrile (NBR)	Neoprene, Chloroprene (CR)	Silicone (VMQ)
Lard, Animal Fats	U	U	U	BC	AB	A	B	AB
Lavendar Oil	U	U	U	U	U	B	U	U
Lead Acetate	AB	A	U	A	A	AB	AB	U
Lead Nitrate	A	A	A	A	A	A	A	B
Lead Sulfamate	B	B	B	A	A	B	A	B
Lehigh X1169	U	U	U	U	U	A	B	U
Lehigh X1170	U	U	U	U	U	A	B	U
Light Grease	U	U	U	U	U	A	U	U
Ligroin (Petroleum Ether; Benzine)	U	U	U	U	U	A	B/U	U
Lime Bleach	A	A	A	A	A	A	B	B
Lime Sulfur	B/U	B/U	B/U	A	A	A	A	AB
Lindol, Hydraulic Fluid (Phosphate Ester type)	U	U	U	A	A	U	U	C
Linoleic Acid	U	U	U	U	U	B	B/U	B
Linseed Oil	U	U	U	AB	BC	A	A	A
Liquid Oxygen	U	U	U	U	U	U	U	U
Liquified Petroleum Gas (LPG)	U	U	U	U	U	A	AC	U
Liquimoly	U	U	U	U	U	A	B	U
Lubricating Oils, Di-ester	U	U	U	U	U	B	C	
Lubricating Oils, Petroleum Base	U	U	U	U	U	A	B	B/U
Lubricating Oils, SAE 10, 20, 30, 40, 50	U	U	U	U	U	A	B/U	A/U
Lye	A	AB	A	A	A	U	A	A
Lye Solutions		A	B	A	A	A	A	AB
Magnesium Chloride	A	A	A	A	A	A	A	A
Magnesium Hydroxide	A	A	B	A	A	A	A	B
Magnesium Salts	A	A	A	A	A	A	A	A
Magnesium Sulfate (Epsom Salts)	AB	AB	B	A	A	A	A	A
Magnesium Sulfite	B	B	B	A	A	A	A	A
Malathion	U	U	U	U	U	B		U
Maleic Acid	U	U	U	C/U	A	B/U	U	U
Maleic Anhydride	U	U	U	C/U	U	U	U	
Malic Acid	A	A	B	U	U	A	AB	B
MCS 312	U	U	U	U	U	U	U	A
MCS 352	U	U	U	B	A	U	U	C
MCS 463	U	U	U	B	A	U	U	C
Mercuric Chloride	A	A	A	A	A	A	A	A
Mercury	A	A	A	A	A	A	A	A
Mercury Vapors	A/U	A/U	A	A	A	A	A/U	
Mesityl Oxide (Ketone)	U	U	U	B/U	AB	U	U	U
Methane	B/U	BC	B/U	U	U	A	AB	A/U
Methanol	A	A	A	A	AB	AB	B	A
Methyl Acetate	U	U	U	B	AB	U	B/U	U
Methyl Acetoacetate	U	U		B	B	U	U	B
Methyl Acrylate	U	U	U	B	AB	U	B/U	U
Methylacrylic Acid	U	U	U	B	B	U	B	U
Methyl Alcohol	A	A	A	A	A	A	A	A
Methyl Benzoate	U	U	U	U	U	U	U	U
Methyl Bromide	C/U	C/U	U	B/U	A/U	B	U	
Methyl Butyl Ketone	U	U	U	A	A	U	U	U
Methyl Carbonate	U	U	U	U	U	U	U	U
Methyl Cellosolve	U	U	U	B	B	C	B	U
Methyl Cellulose	B	B	B	B	B	B	B	B

A: Recommended; Little or Minor Effect B: Minor to Moderate Effect C: Moderate to Severe Effect U: Unsatisfactory Blank: Insufficient Data

NOTE: This chart is only a general guide. ELBEX cannot guarantee its accuracy nor assume any responsibility for its use thereof. It is recommended that testing is performed for specific applications.

Chemical	Polyisoprene (IR)	Natural Rubber (NR)	Styrene Butadiene (SBR)	Butyl (IIR)	Ethylene Propylene (EP, EPDM)	Nitrile (NBR)	Neoprene, Chloroprene (CR)	Silicone (VMQ)
Methyl Chloride	U	U	U	U	U	U	U	U
Methyl Chloroformate	U	U	U	U	U	U	U	U
Methyl Cyclopentane	U	U	U	U	U	U	U	B
Methyl D-Bromide	U	U	U			U	U	U
Methylene Chloride	U	U	U	U	BC	U	U	U
Methylene Dichloride	U	U	U	U	U	U	U	U
Methyl Ether	A/U	A/U	A	AC	A	A	C	A
Methyl Ethyl Ketone (MEK)	U	U	U	A	A	U	U	U
Methyl Ethyl Ketone Peroxide	U	U	U	U	U	U	U	B
Methyl Formate	U	U	U	B	AB	U	B	B
Methyl Isobutyl Ketone (MIBK)	U	U	U	C	AB	U	U	C/U
Methyl Isopropyl Ketone	U	U	U	B	BC	U	U	B/U
Methyl Methacrylate	U	U	U	B/U	U	U	U	C/U
Methyl Oleate	U	U	U	B	B	U	U	
MIL-L-644B	C	C	C	C	C	A	C	C
MIL-L-2104B	U	U	U	U	U	A	AB	U
MIL-L-2105B	U	U	U	U	U	A	A	C
MIL-L-2108	U	U	U	U	U	A	A	C
MIL-S-3136B, Type I Fuel (ASTM Fuel A)	U	U	U	U	U	A	B	U
MIL-S-3136B, Type II Fuel	U	U	U	U	U	B/U	U	U
MIL-S-3136B, Type III Fuel (ASTM Fuel B)	U	U	U	U	U	B/U	U	U
MIL-S-3136B, Type IV (Low Swell Oil)	U	U	U	U	U	A	A	AC
MIL-S-3136B, Type V (Medium Swell Oil)	U	U	U	U	U	A	B	BC
MIL-S-3136B, Type VI (High Swell Oil)	U	U	U	U	U	A	U	BC
MIL-S-3136B, Type VII	U	U	U	U	U	A	C	U
MIL-L-3150A	U	U	U	U	U	A	B	U
MIL-G-3278	U	U	U	U	U	B	U	U
MIL-L-3503	U	U	U	U	U	A	B	U
MIL-L-3545B	U	U	U	U	U	AB	B	U
MIL-C-4339C	U	U	U	U	U	A	U	C
MIL-G-4343B	A/U	A/U	A/U	AC	AC	AB	AB	C/U
MIL-L-5020A	U	U	U	U	U	A	B	U
MIL-J-5161F	U	U	U	U	U	B	U	U
MIL-C-5545A	U	U	U	U	U	B	B	U
MIL-H-5559A	B	B	A	A	A	A	B	B
MIL-F-5566	A	A	B	A	A	B	B	A
MIL-G-5572	U	U	U	U	U	A	U	U
MIL-F-5602	U	U	U	U		A	B	C
MIL-H-5606B	U	U	U	U	BC	A	B	U
MIL-J-5624G, JP-3	U	U	U	U	U	A	U	U
MIL-J-5624G, JP-4	U	U	U	U	U	A	U	U
MIL-J-5624G, JP-5	U	U	U	U	U	A	U	U
MIL-L-6081C	U	U	U	U	U	A	B	U
MIL-L-6082C	U	U	U	U	U	A	B	AC
MIL-H-6083C	U	B/U	U	U	U	A	AB	U
MIL-L-6085A	U	U	U	U	U	B	U	U
MIL-L-6086B	U	U	U	U	U	A	A	C
MIL-A-6091	A	A	A	A	A	B	A	A
MIL-L-6387	U	U	U	U	U	B	U	U
MIL-C-6529C	U	U	U	U	U	B	B	U
MIL-F-7024	U	U	U	U	U	A	U	U

A: Recommended; Little or Minor Effect B: Minor to Moderate Effect C: Moderate to Severe Effect U: Unsatisfactory Blank: Insufficient Data

NOTE: This chart is only a general guide. ELBEX cannot guarantee its accuracy nor assume any responsibility for its use thereof. It is recommended that testing is performed for specific applications.

Chemical	Polyisoprene (IR)	Natural Rubber (NR)	Styrene Butadiene (SBR)	Butyl (IIR)	Ethylene Propylene (EP, EPDM)	Nitrile (NBR)	Neoprene, Chloroprene (CR)	Silicone (VMQ)
MIL-H-7083	BC	B	B	A	A	A	B	AB
MIL-G-7118A	U	U	U	U	U	B	BC	U
MIL-G-7187	U	U	U	U	U	A	U	U
MIL-G-7421A	U	U	U	U	U	B	BC	U
MIL-H-7644	B	B	A	B	A	B	B	U
MIL-L-7645	U	U	U	U	U	B	B	U
MIL-G-7711A	U	U	U	U	U	A	U	BC
MIL-L-7808F	U	U	U	U	U	A	U	U
MIL-L-7870A	U	U	U	U	U	A	B	U
MIL-C-8188C	U	U	U	U	U	B	U	U
MIL-A-8243B	B	B	A	A	A	A	B	B
MIL-L-8383B	U	U	U	U	U	A	A	C
MIL-H-8446B	U	U	U	U	U	B	AB	U
MIL-I-8660B	A	A	A	A	A	A	A	U
MIL-L-9000F	U	U	U	U	U	A	B	U
MIL-T-9188B	U	U	U	A	A	U	U	U
MIL-L-9263B	C/U	U	U	U	U	B	U	U
MIL-E-9500	A	A	A	A	A	A	A	A
MIL-L-10295A	U	U	U	U	U	A	B	C
MIL-L-10324A	U	U	U	U	U	A	B	C
MIL-G-10924B	U	U	U	U	U	A	U	U
MIL-L-11734B	U	U	U	C	U	A	C	C
MIL-O-11773	U	U	U	C	U	A	C	C
MIL-P-12098	B	B	A	B	A	B	B	U
MIL-H-13862	U	U	U	U	U	A	B	C
MIL-H-13866A	U	U	U	U	U	A	B	C
MIL-H-13910B	AB	AB	A	AB	A	AB	AB	A/U
MIL-H-13919A	U	U	U	U	U	A	B	C
MIL-L-14107B	U	U	U	U	U	C	A	U
MIL-L-15016	U	U	U	U	U	A	B	U
MIL-L-15017	U	U	U	U	U	A	B	U
MIL-L-15018B	U	U	U	U	U	A	A	C
MIL-L-15019C	U	U	U	U	U	A	A	C
MIL-L-15719A	C	C	B	B	B	B	B	U
MIL-L-15793	U	U	U	U	U	A	BC	U
MIL-F-16884	U	U	U	U	U	A	C	U
MIL-F-16929A	U	U	U	C	U	A	C	C
MIL-L-16958A	U	U	U	U	U	A	B	C
MIL-F-17111	U	U	U	U	U	A	B	U
MIL-L-17331D	U	U	U	U	U	A	B	U
MIL-L-17353A	U	U	U	U	U	A	C	C
MIL-L-17672B	U	U	U	U	U	A	A	C
MIL-L-18486A	U	U	U	U	U	A	A	C
MIL-G-18709A	U	U	U	U	U	A	A	C
MIL-H-19457B	U	U	U	A	A	U	U	C/U
MIL-F-19605	U	U	U	U	U	A	C	U
MIL-L-19701	U	U	U	C	U	A	C	C
MIL-L-21260	U	U	U	U	U	A	B	U
MIL-G-21568A	AB	AB	A	A	A	A	A	U
MIL-H-22072	B	B	A	A	A	A	B	B
MIL-H-22251			B	A	A	B	B	U

A: Recommended; Little or Minor Effect B: Minor to Moderate Effect C: Moderate to Severe Effect U: Unsatisfactory Blank: Insufficient Data

NOTE: This chart is only a general guide. ELBEX cannot guarantee its accuracy nor assume any responsibility for its use thereof. It is recommended that testing is performed for specific applications.

Chemical	Polyisoprene (IR)	Natural Rubber (NR)	Styrene Butadiene (SBR)	Butyl (IIR)	Ethylene Propylene (EP, EPDM)	Nitrile (NBR)	Neoprene, Chloroprene (CR)	Silicone (VMQ)
MIL-L-22396	U	U	U	U	U	A	A	C
MIL-L-23699A	U	U	U	U	U	B	C	U
MIL-G-23827A	U	U	U	C	U	A	C	C
MIL-G-25013D	U	U	U	U	U	A	B	U
MIL-F-25172	U	U	U	U	U	A	C	U
MIL-L-25336B	U	U	U	C	U	A	C	C
MIL-F-25524A	U	U	U	U	U	A	C	U
MIL-G-25537A	U	U	U	U	U	A	B	U
MIL-F-25558A	U	U	U	U	U	A	B	U
MIL-F-25576C	U	U	U	U	U	A	BC	U
MIL-H-25598	U	U	U	U	U	A	B	C
MIL-F-25656B	U	U	U	U	U	AB	U	U
MIL-L-25681C	B	B	B	A	A	B	B	U
MIL-G-25760A	C/U	U	U	U	U	B	BC	U
MIL-L-25968	U	U	U	C	U	A	C	C
MIL-L-26087A	U	U	U	U	U	A	A	C
MIL-G-27343	A	A	A	A	A	A	A	U
MIL-P-27402			B	A	A	B	B	U
MIL-H-27601A	U	U	U	U	U	AB	B	C/U
MIL-G-27617			B	A	A	U		U
MIL-I-27686D	B	B	A	A	A	A	B	B
MIL-L27694A	A	A	A	A	A	A	A	U
MIL-L-46000A	U	U	U	C	U	A	C	C
MIL-H-46001A	U	U	U	U	U	A	A	C
MIL-L-46002	U	U	U	U	U	A	A	C
MIL-H-46004	U	U	U	U	U	A	B	C
MIL-P-46046A	B	B	A	B	A	B	B	U
MIL-H-81019B	U	U	U	U	U	A	B	C
MIL-S-81087	A	A	A	A	A	A	A	C/U
MIL-H-83282	U	U	U	U	U	A	B	U
Milk	A	A	A	A	A	A	A	A
Mineral Oils	U	U	U	C/U	U	A	A	B
Mobil 24 DTE	U	U	U	U	U	A	B	U
Mobil HF	U	U	U	U	U	A	B	U
Mobil Delvac 1100,1110,1120,1130	U	U	U	U	U	A	B	U
Mobil Nyvac 20 and 30	A	A	A	A	A	A	A	A
Mobil Velocite C	U	U	U	U	U	A	B	U
Mobilgas WA200, Type A, Auto. Trans. Fluid	U	U	U	U	U	A	B	U
Mobil Oil SAE 20	U	U	U	U	U	A	B	U
Mobiltherm 600	U	U	U	U	U	A	B	U
Mobilux	U	U	U	U	U	A	B	U
Monobromobenzene	U	U	U	U	U	U	U	U
Monochlorobenzene	U	U	U	U	U	U	U	U
Monoethanolamine	B	B	B	B	AB	B	B	B
Monomethyl Aniline	A/U	A/U	U	A/U	A/U	A/U	U	
Monomethyl Ether	B/U	B/U	B	A	A	A	AB	
Monomethyl Hydrazine			B	A	A	B	B	U
Mononitrotoluene & Dinitrotoluene (40/60 Mix)	U	U	U	U	U	U	U	U
Monovinyl Acetate	U	U	U	A	B	U	U	U
Mopar Brake Fluid			A	B	A	C	B	C
Mustard Gas	A	A		A	A		A	A

A: Recommended; Little or Minor Effect B: Minor to Moderate Effect C: Moderate to Severe Effect U: Unsatisfactory Blank: Insufficient Data

NOTE: This chart is only a general guide. ELBEX cannot guarantee its accuracy nor assume any responsibility for its use thereof. It is recommended that testing is performed for specific applications.

Chemical	Polyisoprene (IR)	Natural Rubber (NR)	Styrene Butadiene (SBR)	Butyl (IIR)	Ethylene Propylene (EP, EPDM)	Nitrile (NBR)	Neoprene, Chloroprene (CR)	Silicone (VMQ)
Naptha	U	U	U	U	U	A	U	U
Napthalene	U	U	U	U	U	U	U	U
Napthenic Acid	U	U	U	U	U	B	U	U
Natural Gas	BC	BC	BC	U	U	A	A	A/U
Neatsfoot Oil	U	U	U	B	B	A	U	B
Neon	A	A	A	A	A	A	A	A
Neville Acid	U	U	U	B	B	U	U	U
Nickel Acetate	A	A	U	A	A	AB	B	U
Nickel Chloride	A	A	A	A	A	A	AB	A
Nickel Salts	A	A	A	A	A	A	AB	A
Nickel Sulfate	AB	AB	B	A	A	A	A	A
Niter Cake	A	A	A	A	A	A	A	A
Nitric Acid, 3 Molar	U	U	U	A	B	U	U	U
Nitric Acid, Concentrated	U	U	U	C	U	U	U	U
Nitric Acid, Dilute	U	U	U	B	B	U	A	B
Nitric Acid, Inhibited Red Fuming (IRFNA)	U	U	U	B/U	U	U	U	U
Nitric Acid, Red Fuming (RFNA)	U	U	U	B/U	U	U	U	U
Nitrobenzene	U	U	U	B	AB	U	U	A
Nitrobenzine	U	U		C	U	A	B/U	A
Nitroethane	B	B	B	B	B	U	BC	U
Nitrogen, Gas	A	A	A	A	A	A	A	A
Nitrogen Textroxide (N2O4)	U	U	U	BC	B/U	U	U	U
Nitromethane	B	B	B/U	B	AB	U	C/U	U
1-Nitropropane	U	U	U	B	B	U	U	U
O-A-548A	B	B	A	A	A	A	B	B
O-T-634B	U	U	U	U	U	C	U	U
Octachlorotoluene	U	U	U	U	U	U	U	U
Octadecane	U	U	U	U	U	A	B	U
n-Octane	U	U	U	U	U	B	U	U
Octyl Alcohol	B	B	AB	B	AB	AB	AB	B
Oleic Acid	U	U	U	U	BC	A	BC	U
Oleum (Red Fuming Sulfuric Acid)	U	U	U	U	U	U	U	U
Oleum Spirits	U	U	U	U	U	B	C/U	U
Olive Oil	U	U	U	B	B	A	B	A/U
Oronite 8200, 8515	U	U	U	U	U	B	A	U
Orthoboric Acid	A	A	A	A	A	A	A	A
Orthochloroethylbenzene	U	U	U	U	U	U	U	U
Orthodichlorobenzene	U	U	U	U	U	U	U	U
OS 45 Type III, Silicate Ester Base	U	U	U	A/U	U	B	A	U
OS 45 Type IV	U	U	U	U	U	B	A	U
OS 70	U	U	U	U	U	B	A	U
Oxalic Acid	B	BC	B	A	A	AB	B	B
Oxygen, Cold	B	B	B/U	A	A	B	A	A
Oxygen, Hot	U	U	U	U	U	U	U	B
Ozone	U	U	C/U	B	A	U	BC	A
P-D-680	U	U	U	U	U	A	C	U
P-S-661B	U	U	U	U	U	A	C	U
Paint Thinner, Duco	U	U	U	U	U	U	U	U
Palmitic Acid	AB	A	B	B	B	A	B	U
Para-dichlorobenzene	U	U	U	U	U	U	U	U
Par-al-Ketone	U	U	U	U	U	U	U	U

A: Recommended; Little or Minor Effect B: Minor to Moderate Effect C: Moderate to Severe Effect U: Unsatisfactory Blank: Insufficient Data

NOTE: This chart is only a general guide. ELBEX cannot guarantee its accuracy nor assume any responsibility for its use thereof. It is recommended that testing is performed for specific applications.

Chemical	Polyisoprene (IR)	Natural Rubber (NR)	Styrene Butadiene (SBR)	Butyl (IIR)	Ethylene Propylene (EP, EPDM)	Nitrile (NBR)	Neoprene, Chloroprene (CR)	Silicone (VMQ)
Parker O Lube	U	U	B	U	U	A	A	B
Peanut Oil	U	U	U	C	C	A	B/U	A
N-Pentane	U	U	C	U	U	A	A	U
n-Pentane, 2 Methyl, 2-4 Methyl, & 3 Methyl	U	U	U	U	U	A	B	U
Pentanol	A	A		A	A	A	A	U
Pentasol	A	A	B	A	A	AB	A	U
Perchloric Acid	U	U	U	B	B	U	AB	U
Perchloroethylene	U	U	U	U	U	B/U	U	B/U
Petroleum, Crude	U	U	U	U	U	A	B	U
Petroleum Oils	U	U	U	U	U	A	B	B
Phenic Acid	U	U		B	C	U	C	U
Phenol	U	U	U	B	U	U	U	U
Phenolsulfonic Acid	U	U		C		U		
Phenyl Acetate	C	C/U		B	B	U	U	U
Phenylbenzene	U	U	U	U	U	U	U	U
Phenyl Ethyl Ether	U	U	U	U	U	U	U	U
Phenyl Hydrazine	A	A	B	U	C/U	U	U	
Phorone	U	U	U	AB	AB	U	U	U
Phosphoric Acid 20%	B	B	C	B	A	U	B	BC
Phosphoric Acid 45%	U	U	U	B	B	U	B	C/U
Phosphoric Acid, 3 Molar	B	B	B	B	A	U	C	B
Phosphoric Acid, Concentrated	C	C/U	AB	AB	A	U	B/U	C/U
Phosphorous Trichloride	U	U	U	A	A	U	U	
Pickling Solution	C/U	U	U	C	C	U	U	U
Picric Acid, H2O Solution	AB	AB	B	AB	AB	AB	A	U
Picric Acid, Molten	BC	BC	B		BC	BC	B	U
Pine Oil	U	U	U	U	U	AB	U	U
Pinene	U	U	U	U	U	B	C/U	U
Piperidine	U	U	U	U	U	U	U	U
Plating Solutions, Chrome	U	U	U	A/U	A	U	U	U
Plating Solutions, Others	A	A	A	A	A	A	A	U
Pneumatic Service	U	U	U	A	A	A	A	U
Polyvinyl Acetate Emulsion				A	A	A	B	U
Potassium Acetate	A	A	U	A	A	B	B	U
Potassium Chloride	A	A	A	A	A	A	A	A
Potassium Cupro Cyanide	A	A	A	A	A	A	A	A
Potassium Cyanide	A	A	A	A	A	A	AB	A
Potassium Dichromate	A/U	A/U	AB	A	A	A	A	A
Potassium Hydroxide	B	B	B	A	A	AB	AB	C
Potassium Nitrate	A	A	A	A	A	A	A	A
Potassium Salts	A	A	A	A	A	A	A	A
Potassium Sulfate	A	A	B	A	A	A	A	A
Potassium Sulfite	AB	AB	B	A	A	A	A	A
Prestone Antifreeze	A	A	A	A	A	A	AC	A
PRL-High Temp. Hydro. Oil	U	U	U	U	U	B	B	B
Producer Gas	U	U	U	U	U	A	B	B
Propane	U	U	U	U	U	A	AC	U
Propane Propionitrile	U	U	U	U	U	A	B	U
Propyl Acetate	U	U	U	AB	B	U	U	U
n-Propyl Acetone	U	U	U	A	A	U	U	U
Propyl Alcohol	A	A	A	A	A	A	A	A

A: Recommended; Little or Minor Effect B: Minor to Moderate Effect C: Moderate to Severe Effect U: Unsatisfactory Blank: Insufficient Data

NOTE: This chart is only a general guide. ELBEX cannot guarantee its accuracy nor assume any responsibility for its use thereof. It is recommended that testing is performed for specific applications.

Chemical	Polyisoprene (IR)	Natural Rubber (NR)	Styrene Butadiene (SBR)	Butyl (IIR)	Ethylene Propylene (EP, EPDM)	Nitrile (NBR)	Neoprene, Chloroprene (CR)	Silicone (VMQ)
Propyl Nitrate	U	U	U	B	B	U	U	C/U
Propylene	U	U	U	U	U	U	U	U
Propylene Oxide	U	U	U	B	B	U	U	U
Pyranol, Transformer Oil	U	U	U	U	U	A	B	B/U
Pyranol	U	U	U	U	U	A	U	U
Pydraul 10E	U	U	U	AB	AB	U	U	U
Pydraul 29ELT, 30E, 50E, 65E, 90E	U	U	U	AB	AB	U	U	A
Pydraul, 115E	U	U	U	AB	AB	U	U	U
Pydraul 230C, 312C, 540C	U	U	U	U	U	U	U	U
Pyridine Oil	U	U	U	B	B	U	U	U
Pyrogard 42,43,53,55 (Phosphate Ester)	U	U	U	A	A	U	U	U
Pyrogard C & D (Water and Petroleum)	U	U	U	U	U	A	B	B
Pyroligneous Acid	U	U	U	B	B	U	U	A
Pyrolube	U	U	U	B	B	U	U	B
Pyrrrole	BC	BC	BC	U	U	U	U	B
Radiation	BC	BC	C	U	BC	BC	BC	AB
Rapeseed Oil	U	U	U	A	A	AB	B	U
Red Line 100 Oil	U	U	U	U	BC	A	BC	U
Red Oil (MIL-H-5606)	U	U	U	U	U	A	B	U
RJ-1 (MIL-F-25558)	U	U	U	U	U	A	B	U
RP-1 (MIL-R-25576)	U	U	U	U	U	A	BC	U
Sal Ammoniac	A	A	A	A	A	A	A	BC
Salicylic Acid	A	A	B	A	A	AB	C/U	
Salt Water	A	A	A	A	A	A	A	A
Santo Safe 300	U	U	U	C	C	U	U	A
Sewage	AB	AB	AB	AB	A	A	AB	AB
Shell Alvania Grease #2	U	U	U	U	U	A	B	B
Shell Carnea 19 and 29	U	U	U	U	U	A	U	
Shell Diala	U	U	U	U	U	A	B	U
Shell Iruis 905	U	U	U	U	U	A	A	U
Shell 3XF Mine Fluid (Fire Resist. Hydro.)	U	U	U	U	U	A	B	
Shell Tellus #27, Pet. Base	U	U	U	U	U	A	B	U
Shell Tellus #33	U	U	U	U	U	A	B	U
Shell UMF (5% Aromatic)	U	U	U	U	U	A	B	U
Shell Lo Hydrax 27 and 29	U	U	U	U	U	A	B	U
Shell Macoma 72	U	U	U	U	U	A	B	U
Silicate Esters	U	U	U	B/U	U	AB	A	U
Silicone Greases	A	A	A	A	A	A	A	BC
Silicone Oils	AC	AC	A	A	A	A	A	C/U
Silver Nitrate	A	A	A	A	A	AB	A	A
Sinclair Opaline CX-EP Lube	U	U	U	U	U	A	B	U
Skelly, Solvent, B, C, E	U	U	U	U	U	A	U	
Skydrol 500	U	U	U	AB	A	U	U	C
Skydrol 7000	U	U	U	A	A	U	U	B/U
Soap Solutions	AB	B	B	AB	A	A	AB	A
Socony Mobile Type A	U	U	U	U	U	A	B	U
Socony Vacuum AMV AC781 (Grease)	U	U	U	U	U	A	B	U
Socony Vacuum PD959B	U	U	U	U	U	A	B	U
Soda Ash	A	A	A	A	A	A	A	A
Sodium Acetate	A	A	U	A	A	AB	AB	U
Sodium Bicarbonate (Baking Soda)	A	A	A	A	A	A	A	A

A: Recommended; Little or Minor Effect B: Minor to Moderate Effect C: Moderate to Severe Effect U: Unsatisfactory Blank: Insufficient Data

NOTE: This chart is only a general guide. ELBEX cannot guarantee its accuracy nor assume any responsibility for its use thereof. It is recommended that testing is performed for specific applications.

Chemical	Polyisoprene (IR)	Natural Rubber (NR)	Styrene Butadiene (SBR)	Butyl (IIR)	Ethylene Propylene (EP, EPDM)	Nitrile (NBR)	Neoprene, Chloroprene (CR)	Silicone (VMQ)
Sodium Bisulfite	AB	A	B	A	A	A	A	A
Sodium Borate	A	A	A	A	A	A	A	A
Sodium Carbonate (Soda Ash)	A	A	A	A	A	A	A	A
Sodium Chloride	A	A	A	AB	A	A	A	A
Sodium Cyanide	A	A	A	A	A	A	A	A
Sodium Hydroxide	A	A	A	A	A	B/U	A	A
Sodium Hypochlorite	BC	C/U	BC	B	AB	B/U	B/U	B
Sodium Metaphosphate	A	A	A	A	A	A	B	
Sodium Nitrate	AB	B	B	A	A	AB	B	C/U
Sodium Perborate	B	B	B	A	A	B	B	B
Sodium Peroxide	B	B	B	A	A	B	B	C/U
Sodium Phosphate (Mono)	A	A	A	A	A	A	AB	U
Sodium Phosphate (Dibasic)	A	A	A	A	A	A	BC	U
Sodium Phosphate (Tribasic)	A	A	A	A	A	A	BC	A
Sodium Salts	A	A	A	A	AB	A	AB	A
Sodium Silicate	A	A	A	A	A	A	A	A
Sodium Sulfate	AB	AB	B	A	A	A	A	A
Sodium Sulfide	AB	AB	B	A	A	A	A	A
Sodium Sulfite	AB	AB	B	A	A	A	A	A
Sodium Thiosulfate	AB	AB	B	A	A	AB	A	A
Solvasol #1,2, and 3	U	U	U	U	U	A	B	U
Solvasol #73 and 74	U	U	U	U	U	B	B	U
Soybean Oil	U	U	U	AC	U	A	A	A
Spry	U	U	U	B	B	A	B	A
SR-6 Fuel	U	U	U	U	U	B	U	U
SR-10 Fuel	U	U	U	U	U	A	U	U
Standard Oil Multilube GX90-EP	U	U	U	U	U	A	B	U
Stannic Chloride	A	A	A	AB	A	A	BC	B
Stannic Chloride 50%	A	A	A	B	B	A	U	B
Stannous Chloride	A	A	A	AB	BC	A	A	B
Stauffer 7700	U	U	U	U	U	B	U	U
Steam, 212 F						U	C	
Steam, 225 F	C	C	B					B/U
Steam, 300 F	U	U	U					C/U
Steam, 350 F				B	A	C/U		U
Steam, 450 F				C/U	B		C/U	
Steam and Hot Water			U		A	U	A/U	U
Stearic Acid	B/U	B/U	B	B	B	A	B	B
Stoddard Solvent	U	U	U	U	U	A	BC	U
Styrene (Monomer)	U	U	U	U	U	U	U	U
Styrene (Polymer)	U	U	U	U	U	U	U	U
Sucrose Solutions	A	A	A	A	A	A	A	A
Sulfite Liquors	B	B	B	B	B	AB	AB	U
Sulfur Chloride	U	U	U	U	U	C/U	C/U	C
Sulfur Dioxide Gas, Dry	BC	BC	BC	B	A	U	U	AB
Sulfur Dioxide Gas, Wet	U	B/U	B/U	A	A	U	B	B
Sulfur Dioxide, Liquid	B	B	U	B	A	U	A/U	B
Sulfur Dioxide, Pressurized	U	U	U	B	A	U	U	B
Sulfur Hexafluoride	U	U	U	A	A	B	A	B
Sulfur Liquors	B	B	B	B	B	B	B	U
Sulfur (Molten 250 F)	C/U	C/U	U	A	A	U	A	AC

A: Recommended; Little or Minor Effect B: Minor to Moderate Effect C: Moderate to Severe Effect U: Unsatisfactory Blank: Insufficient Data

NOTE: This chart is only a general guide. ELBEX cannot guarantee its accuracy nor assume any responsibility for its use thereof. It is recommended that testing is performed for specific applications.

Chemical	Polyisoprene (IR)	Natural Rubber (NR)	Styrene Butadiene (SBR)	Butyl (IIR)	Ethylene Propylene (EP, EPDM)	Nitrile (NBR)	Neoprene, Chloroprene (CR)	Silicone (VMQ)
Sulfur Trioxide	B	BC	C/U	B	BC	U	U	B
Sulfuric Acid, Dilute	A	A	C	A	A	A/U	B	B/U
Sulfuric Acid, Concentrated	U	U	U	U	U	U	U	U
Sulfuric Acid, (20-25% Oleum)	U	U	U	U	U	U	U	U
Sulfuric Acid, 3 Molar	C	C	C	C	B	U	C	U
Sulfurous Acid	B	B/U	B	AB	AB	B/U	C/U	U
Sunoco SAE 10	U	U	U	U	U	A	B	U
Sunoco #3661	U	U	U	U	U	A	B	U
Sunoco All-Purpose Grease	U	U	U	U	U	A	B	U
Sunsaft (Fire Resist. Hydr. Fluid)	U	U	U	U	U	A	B	
Super Shell Gas	U	U	U	U	U	A	B	U
Swan Finch EP Lube	U	U	U	U	U	A	B/U	U
Swan Finch Hypoid-90	U	U	U	U	U	A	B	U
TT-N-95A	U	U	U	U	U	A	C	U
TT-N-97B	U	U	U	U	U	B	C	U
TT-I-735B	A	A	A	A	A	A	B	A
TT-S-735, Type I	U	U	U	U	U	A	B	U
TT-S-735, Type II	U	U	U	U	U	A	C	U
TT-S-735, Type III	U	U	U	U	U	A	C	U
TT-S-735, Type IV	U	U	U	U	U	A	A	C
TT-S-735, Type V	U	U	U	U	U	A	B	C
TT-S-735, Type VI	U	U	U	U	U	A	B	C
TT-S-735, Type VII	U	U	U	U	U	A	C	U
TT-T-656B	U	U	U	A	A	U	U	U
Tannic Acid (Tannin)	A	A	B	A	A	A	A	B
Tar, Bituminous	B/U	C/U	U	U	U	B	C	B
Tartaric Acid	A	A	B	B	BC	A	A	A
Terpineol	U	U	U	C/U	C	B	U	
Tertiary Butyl Alcohol	B	B	B	B	B	AB	B	B
Tertiary Butyl Catechol	U	U	C	B	B	U	B	
Tertiary Butyl Mercaptan	U	U	U	U	U	U	U	U
Tetrabromomethane	U	U	U	U	U	U	U	U
Tetrabutyl Titanate	B	B	B	B	A	B	AB	
Tetrachloroethylene	U	U	U	U	U	B/U	U	B/U
Tetraethyl Lead	U	U	U	U	U	B	BC	
Tetraethyl Lead Blend	U	U	U	U	U	B	U	
Tetrahydrofuran	U	U	U	B	U	U	U	U
Tetralin	U	U	U	U	U	U	U	U
Texaco 3450 Gear Oil	U	U	U	U	U	A	U	U
Texaco Capella A and AA	U	U	U	U	U	A	B	U
Texaco Meropa 220 #3 (No Lead)	U	U	U	U	U	A	B	U
Texaco Regal B	U	U	U	U	U	A	U	U
Texaco Uni-Temp. Grease	U	U	U	U	U	A	B	B
Texamatic 1581 Fluid	U	U	U	U	U	A	B	U
Texamatic 3401 Fluid	U	U	U	U	U	A	B	U
Texamatic 3525 Fluid	U	U	U	U	U	A	B	U
Texamatic 3528 Fluid	U	U	U	U	U	A	B	U
Texas 1500 Oil	U	U	U	U	U	A	B	B
Thiokol TP-90B			U	A	A	U	B	
Thiokol TP-95			U	A	A	U	B	
Thionyl Chloride	U	U		U	U	U	U	U

A: Recommended; Little or Minor Effect B: Minor to Moderate Effect C: Moderate to Severe Effect U: Unsatisfactory Blank: Insufficient Data

NOTE: This chart is only a general guide. ELBEX cannot guarantee its accuracy nor assume any responsibility for its use thereof. It is recommended that testing is performed for specific applications.

Chemical	Polyisoprene (IR)	Natural Rubber (NR)	Styrene Butadiene (SBR)	Butyl (IIR)	Ethylene Propylene (EP, EPDM)	Nitrile (NBR)	Neoprene, Chloroprene (CR)	Silicone (VMQ)
Tidewater Oil-Beedol	U	U	U	U	U	A	B	B
Tidewater Oil-Multigear 140, EP Lube	U	U	U	U	U	A	B	U
Titanium Tetrachloride	U	U	U	U	U	B/U	U	U
Toluene	U	U	U	U	U	U	U	U
Toluene Diisocyanate (Hylene)	C/U	C/U	U	AB	AB	U	U	U
Transformer Oil	U	U	U	U	U	A	B	B
Transmission Fluid Type A	U	U	U	U	U	A	B	B
Triacetin	B	B	C	A	A	B	B	
Triaryl Phosphate	U	U	U	A	A	U	U	C
Tributoxy Ethyl Phosphate	B/U	B	B	A	A	U	U	
Tributyl Mercaptan	U	U	U	U	U	U	U	U
Tributyl Phosphate	B	B/U	U	B	A	U	U	C/U
Trichloroacetic Acid	BC	BC	U	B	B	B/U	U	U
Trichloroethane	U	U	U	U	U	U	U	U
Trichloroethylene	U	U	U	U	U	U	U	U
Tricresyl Phosphate	C/U	BC	U	A	A	U	BC	C
Triethanolamine	B	B	B	AB	B	BC	U	
Triethyl Aluminum	U	U				U	U	
Triethyl Borane	U	U				U	U	
Trifluoroethane	U	U	U	U	U	U	U	U
Trinitrotoluene	U	U	U	U	U	U	A	C
Trioctyl Phosphate	U	U	U	A	A	U	B/U	C
Tripolyphosphate	U	U	U	A	A	U	B	C
Tung Oil (China Wood Oil)	U	U	U	B/U	U	A	A	U
Turbine Oil	U	U	U	U	U	AB	B	U
Turbine Oil #15 (MIL-L-7808A)	U	U	U	U	U	AB	U	A
Turbo Oil #35	U	U	U	U	U	A	B	U
Turpentine	U	U	U	U	U	A	U	U
Type I Fuel (MIL-S-3136)	U	U	U	U	U	A	B	U
Type II Fuel (MIL-S-3136)	U	U	U	U	U	B/U	U	U
Type III Fuel (MIL-S-3136)	U	U	U	U	U	B/U	U	U
Ucon Hydrolube J-4			A	A	A	A	B	A
Ucon Lubricant LB-65	B	B	B	A	A	A	A	A
Ucon Lubricant LB-135	A	A	A	A	A	A	A	A
Ucon Lubricant LB-285	A	A	A	A	A	A	A	A
Ucon Lubricant LB-300	A	A	A	A	A	A	A	A
Ucon Lubricant LB-625	A	A	A	A	A	A	A	A
Ucon Lubricant LB-1145	A	A	A	A	A	A	A	A
Ucon Lubricant 50-HB55	A	A	A	A	A	A	A	A
Ucon Lubricant 50-HB100	A	A	A	A	A	A	A	A
Ucon Lubricant 50-HB260	A	A	A	A	A	A	A	A
Ucon Lubricant 50-HB660	A	A	A	A	A	A	A	A
Ucon Lubricant 50-HB5100	A	A	A	A	A	A	A	A
Ucon Oil LB-385	A	A	A	A	A	A	A	A
Ucon Oil LB-400X	A	A	A	A	A	A	A	A
Ucon Oil 50-HB-280X (Polyacrylon Glycol De.)	A	A	A	A	A	A	A	A
Univis 40 (Hydr. Fluid)	U	U	U	U	U	A	B	U
Univolt #35 (Mineral Oil)	U	U	U	U	U	A	B	U
Unsymmetrical Dimethyl Hydrazine (UDMH)	A	A	B/U	A	A	B	B	U
VV-B-680	B	B	A	B	A	B	B	U
VV-G-632	U	U	U	U	U	A	A	C

A: Recommended; Little or Minor Effect B: Minor to Moderate Effect C: Moderate to Severe Effect U: Unsatisfactory Blank: Insufficient Data

NOTE: This chart is only a general guide. ELBEX cannot guarantee its accuracy nor assume any responsibility for its use thereof. It is recommended that testing is performed for specific applications.

Chemical	Polyisoprene (IR)	Natural Rubber (NR)	Styrene Butadiene (SBR)	Butyl (IIR)	Ethylene Propylene (EP, EPDM)	Nitrile (NBR)	Neoprene, Chloroprene (CR)	Silicone (VMQ)
VV-G-671C	U	U	U	U	U	A	A	C
VV-H-910	B	B	A	B/U	A	C	B	B/U
VV-I-530A	U	U	U	U	U	A	B	C
VV-K-211D	U	U	U	U	U	A	C	U
VV-K-220A	U	U	U	U	U	A	B	U
VV-L-751B	U	U	U	U	U	B	B	U
VV-L-800	U	U	U	U	U	A	B	C
VV-L-820B	U	U	U	U	U	A	B	C
VV-L-825A, Type I	U	U	U	U	U	A	A	C
VV-L-825A, Type II	U	U	U	U	U	A	A	C
VV-L-825A, Type III	U	U	U	U	U	B	B	U
VV-O-526	U	U	U	U	U	A	A	C
VV-P-216A	U	U	U	U	U	A	B	C
VV-P-236	U	U	U	U	U	B	B	U
Varnish	U	U	U	U	U	B/U	U	U
Vegetable Oil	U	U	U	AC	AC	A	B/U	A
Versilube F44, F50, & F55	A	A	A	A	A	A	A	C
Vinegar	B	B	B	A	A	B	B	A
Vinyl Chloride Gas		AB		U	B			
Vinyl Chloride Liquid	C	BC		B	BC	U	U	
Wagner 21B Brake Fluid			A	B	A	C	AB	C
Water, Acid Mine	A	AB	U	A	A	A	C	AB
Water, Brine (Process Beverage)				AB	A	A	A	A
Water, Deionized	A	A		A	A	A	A	
Water, Detergent Solution			B		A	B	C	B
Water, Distilled	A	A		A	A	A	AC	C
Water, Fresh	A	A	AB	A	A	A	AB	B
Water, Salt	A	A	A	A	A	A	A	A
Water, Sea	A	A	A	A	A	A	AB	A
Water, Soap Solution			B		A	B	C	U
Water, Soluble Oil Solution			U		U	A	A	
Wemco C	U	U	U	U	U	A	B	U
Whiskey	A	A	A	A	A	A	A	A
White Oil	U	U	U	U	U	A	B	U
White Pine Tar	U	U	U	U	U	B	U	U
Wines	A	A	A	A	A	A	A	A
Wolmar Salt	A	A	A	A	A	A	B	A
Wood Alcohol	A	A	A	A	A	A	A	A
Wood Oil	U	U			U	A	B	U
Xylene	U	U	U	U	U	U	U	U
Xylidenes - Mixed Aromatic Amines	U	U	U	U	U	C/U	U	U
Xylol	U	U	U	U	U	U	U	U
Xenon	A	A	A	A	A	A	A	A
Zeolites	A	A	A	A	A	A		A
Zinc Acetate	A	A	U	A	A	AB	B	U
Zinc Chloride	A	A	A	A	A	A	A	AB
Zinc Salts	A	A	A	A	A	A	A	A
Zinc Sulfate	AB	B	B	A	A	A	A	A
Zinc Sulphate	AB	AB	B	A	A	A	A	A

A: Recommended; Little or Minor Effect B: Minor to Moderate Effect C: Moderate to Severe Effect U: Unsatisfactory Blank: Insufficient Data